



HYPERFORM®



PRODUCT ADVANTAGES

- ✓ **RAPID-SETTING**
- ✓ **HIGH EARLY AND ULTIMATE STRENGTHS**
- ✓ **NON-SHRINKING & NO CALCIUM CHLORIDE**
- ✓ **READY TO USE — JUST ADD WATER**
- ✓ **EXCELLENT RESISTANCE TO FREEZE THAW**

PART NUMBER	DESCRIPTION
QUAD-HF-50	Hyperform® - Fast Curing Cement - #50 Pail
QUAD-HF-60	Hyperform® - Fast Curing Cement - #60 Bag

DESCRIPTION

Hyperform® (White Lid) is a one component, rapid setting, high early strength patching material designed for repairing vertical and horizontal concrete and masonry structures.

PHYSICAL PROPERTIES

COMPRESSIVE STRENGTH (ASTM C39):

30 minutes >1,200 psi | 8.27 MPa
 1 hour >2,500 psi | 17.24 MPa
 1 day >4,000 psi | 27.58 MPa
 28 days >7,000 psi | 48.26 MPa

BOND STRENGTH (ASTM C882): 28 day >3,000 psi | 20.68 MPa

SHRINKAGE (ASTM C596): 28 Days ≤ 0.02%

YIELD: One 60 lb. | 27.2 kg. bag will yield approximately 0.48 cu. ft. | 0.013 cu. m. and will cover 11.5 sq. ft. | 1.07 sq. m. at a 0.5 in. | 12.7 mm thickness.

RECOMMENDED FOR

- Filling large voids in manhole walls
- Reconstructing inverts & Pipe repair
- Concrete repair and patching

APPLICATION INFORMATION

Prepare surface to be patched by removing all loose concrete by using an air or electric hammer. Next, sandblast or water blast surface to clean away all contaminants, such as oil, chemicals, or dust. Then rinse with potable water to remove all remaining dirt, sand and loose debris.

CEMENTITIOUS



877-450-3701



S1EONLINE.COM



SERVICE@S1EONLINE.COM